



Everyday Snag Resistant Ladies' Polo

L365

Product Features:

- 6.9-oz, 100% performance polyester micropique

Ladies' sizes: XS-3XL



4-button placket with dyed-to-match buttons



Available Colours and PMS Colours

Textile fabric colours are subject to dye lot variation and will not be exact match to print pantone reference



BLACK
Black 6C



WHITE
No PMS



IRON GREY
7540C



SILVER
429C



TRUE NAVY
539C



TRUE ROYAL
7686C



BRIGHT BLUE
7461C



PURPLE
7672C



MAROON
504C



RED
201C



ORANGE
172C



SAFETY ORANGE
No PMS



SAFETY YELLOW
No PMS



GOLD
7549C



FOREST GREEN
7736C



DUCK BROWN
7574C

L365 - Everyday Snag Resistant Ladies' Polo

Garment Measurements

Size	XS	S	M	L	XL	2XL	3XL
Chest - Half Measure	18"	19"	20"	21 1/2"	23"	24 1/2"	26 1/2"
Chest - Full Measure	36"	38"	40"	43"	46"	49"	53"
Body Length from HPS	26"	26 1/2"	27"	28"	29"	30"	30 1/2"
Sleeve Length - CB	14"	14 1/2"	15"	15 5/8"	16 1/4"	16 7/8"	17 1/2"

Finished measurements in inches. Refer to "How to Measure" guide for detailed information on measurement instructions.

Ladies' General Sizing Guide

Size	XS	S	M	L	XL	2XL	3XL
Numeric Size	2	4-6	8-10	12-14	16	18-20	22
Bust	32"-34"	35"-36"	37"-38"	39"-41"	42"-44"	45"-47"	48"-51"
Waist	24"-25"	26"-27"	28"-30"	30"-32"	33"-35"	36"-38"	40"-42"
Hip	33"-35"	35"-37"	37"-39"	39"-41"	42"-44"	45"-47"	48"-50"
Sleeve Length-CB	30"-30 1/2"	30 1/2"-31"	31 1/2"-32"	32 1/2"-33"	33 1/2"-34"	34"-34 1/2"	34 1/2"-35"

Printing Instructions for Polyester Fabrics

Due to the nature of polyester, special care must be taken throughout the decoration process. Here are some tips to effectively decorate our performance products.

Garment temperature must not exceed 320°F or 160°C.

Exceeding this temperature will cause the fabric to shrink, become wavy or cause dye migration.

Dryer temperature and belt speeds must be changed accordingly for polyester fabric.

If flashing these garments, do not exceed 1-2 seconds. Anything longer may damage the fabric as stated above.

SCREEN PRINTING

- These garments require the use of poly inks that cures at a lower temperature. A Dyno Grey base blocker on all colours and a second white base blocker on all dark colours are recommended. Please consult your ink supplier for more information.
- Polyester requires a longer cooling time than cotton. Avoid overlap of garments and screen-print/heat transfer until the garments are cooled. Failure to cool the fabric prior to stacking into a printer's fold may cause the fabric and applied ink to stick together.

HEAT TRANSFERS

- Poly mark heat transfers need to be created with an anti-migration layer in the design. This process can only be done on white or very light colour shirts. Inks used in printing paper design needs to be darker than the base fabric or colour will migrate with the fabric colour resulting in a bleeding effect.

SUBLIMATION PRINTING

- As noted for the poly mark heat transfers, this process can only be done on white or very light colour shirts. Inks used in printing paper design needs to be darker than the base fabric or colour will migrate with the fabric colour resulting in a bleeding effect.
- If you heat press these garments, you must adjust the time, temperature and pressure. Failure to do so may damage the fabric as stated above.

A test sample run is recommended, especially if you have a large order or if your printer does not specialize in printing on performance fabrics.